

Emitida: 19/11/2019
Actualizada: 26/09/2019

Product: NATURAL COATED C1S

One side coated paperboard

Parámetros	Unidades	Método de prueba	Substancias		Tolerancia
Gramaje	g/m2 Tolerance 5%	Tappi 410	281	308	+/- 5%
Grosor	microns/10 Tolerance 5%	Tappi 411	38.1	43.2	+/- 5%
Rigidez Tab CD	g.cm	Tappi 489	57	63	+/- 15%
Rigidez Tab MD	g.cm	Tappi 489	92	115	+/- 15%
Calibre	Pts		15	17	+/- 5%
Rugosidad	microns	Tappi 555	3.5	3.5	
Brillo 75° FS	%	Tappi 480	40		
Lisura	%	Tappi 412	7.2		+/- 0.5

*Certificado ISEGA

* Recubrimiento de color natural

* Fibra virgen de caña de azúcar

* Las condiciones de prueba se controlan a una temperatura de 23 ± 2 ° C y una humedad relativa de $50 \pm 5\%$ según lo establecido en Tappi T-402

Aplicaciones:

Estuchería de lujo

Estuchería de productos
saludables y de belleza

Envases de confitería

Envases farmacéuticos

Envases de cuidado de personal

